

CryoProtect™ Bio-Containers

Storage Solutions for Cryogenic Applications

- Designed for storage, intermediate steps, final fill, and transport in bioprocessing applications
- Used in closed-system processing steps
- Extractables & Leachables (E&L) data available via validation package
- REACH / RoHS compliant

Benefits

- DEHP-free materials
- IPA-compatible
- Compatible with DMSO up to 20%
- Containers tested and validated to -196°C
- Double-Tyvek® cleanroom-compatible packaging
- Industry-standard label pocket design offers ease of use and label traceability



CPB-250

Standard Applications


- Intermediate and final frozen product storage
- Working cell banks
- Biomanufacturing

Custom Design Service

- Customize cryopreservation solutions from concept to prototype
- Compatible with Charter and industry-standard componentry

Ordering Information

Catalog #	Description	Case Qty
CPB-50	CryoProtect™ Bio-Container, 10-30 mL	40
CPB-250	CryoProtect™ Bio-Container, 30-70 mL	40
CPB-500	CryoProtect™ Bio-Container, 55-100 mL	40
CPB-750	CryoProtect™ Bio-Container, 80-190 mL	40



Contact us today at www.chartermedical.com

Film Physical Test Data (pre-gamma irradiation)

Property	Test Protocol	Typical Value(s)
Tensile Strength at Break, MD/TD (psi)	ASTM D882	3,200/2,900
Elongation at Break, MD/TD (%)	ASTM D882	650/700
Modulus at 100% Elongation, MD/TD (psi)	ASTM D882	550/500
Tear Resistance, MD/TD (lbf/in.)	ASTM D1004	200/250
Low Temp. Brittleness (Masland) (°C)	ASTM D1790	Below -100
Glass Transition Temperature (T_g)	DSC	-48°C
Specific Gravity (g/cm³)	ASTM D792	0.92
Particulates	USP <788>	Pass
Oxygen Transmission Rate (cm³/M²/24 hrs @ 23°C, 0% RH)	ASTM D3985	2,200
Carbon Dioxide Transmission Rate (cm³/M²/24 hrs @ 23°C, 0% RH)	ASTM F2476	9,000
Moisture Vapor Transmission (g/M²/24 hrs @ 23°C)	ASTM F1249	3.9

Test performed on 0.014" film


Final Container Biocompatibility Test Data (post-gamma irradiation)

Property	Test Protocol	Typical Value
USP Class VI	USP <88>	Pass
Cytotoxicity	USP <87>/ ISO 10993-5	Pass
Hemolysis	ISO 10993-4	Pass

Drop Test Integrity

Test Description	Testing Criteria	Minimum Sample Size [1]	Testing Pass / Fail
Drop Testing (e.g., leaking)	Resistance to dropping post-thaw from a 1-meter height (ISO 15747:2018 Section 4.1.3)	29[1]	Pass

[1] Defines the sample size for each testing criterion. The sampling plan follows internal SOPs, ensuring a 95% confidence level and 90% reliability, as determined by the risk assessment plan.



CPB-50

Additional Cryogenic and Cold Transportation Studies

Test	Summary of Test	Purpose	Result	Customer Benefit
Long-term Cryogenic Study	Samples were frozen, stored at -192°C for 5 weeks, then tested for leaks and strength	Ensure reliable storage at -192°C with 20% DMSO	Pass	Proven to maintain strength and seal during extended cryogenic storage
Freeze-Thaw Cycling (3x)	Samples went through 3 freeze-thaw cycles, then tested for leaks, drops, and strength	Confirm durability after freezing and thawing	Pass	Reliable even after multiple freeze-thaw cycles, ideal for cryopreservation
Simulated Cold Transportation	Overfilled samples were transported under extreme cold and vibration, then tested	Ensure leak-proof transport under cryogenic conditions	Pass	Leak-proof during transport, supporting reliable cold chain logistics

CryoProtect™ and Freeze-Pak™ are trademarks of Charter Medical, LLC.

Tyvek® is a registered trademark of E.I. du Pont de Nemours and Company or its affiliates.

All data and statements concerning these products may be considered as being indicative of representative properties and characteristics obtainable.

We make no warranty, express or implied, concerning actual use or results because of industry-specific influences.